



CHOICE® ALUMINIZED FABRICS

05PT339-58-AL7

A Norfab woven fabric made of an intimate blend of Twaron®/OPF/Kynol® fibers. The plain weave fabric is aluminized one side. Applications include light weight safety clothing, gloves, mitts, jacket, and other industrial applications. Resistant to reflected heat sources, offers very good thermal protection for safety garments.

About NOR*FAB Corporation

NOR*FAB manufactures textile products using flame resistant synthetic fibers suited for use at high temperatures and for personal protection. These items include broad woven roll goods and narrow products in the form of woven and knitted tapes, sleeving, rope, and gasketing. NOR*FAB uses para-aramid, meta-aramid, melamine, phenolic, oxidized PAN, flame resistant rayon, polybenzimidazole, and other technical fibers blended into unique yarns which provide high levels of heat protection and insulation.

NOR*FAB produces many of these yarns on the DREF Spinning System for use in the weaving, knitting, gasket, and wire & cable industries. NOR*FAB possesses the largest collection of DREF III spinning frames of any yarn manufacturer in the world.

Among its offerings, NOR*FAB boasts fabric lines for the following end uses:

Firefighting

OMNI Vantage™, OMNI Elite®, OMNI 45™, and OMNI Quilt™

Electric Arc Protection

NF Arc™, ArcWeld®

Welding Protection

ArcWeld®

Cut Protection

CutPro®

Molten Metal Splash Protection

Choice®

Since 1979

Proud American Manufacturers of Flame Resistant Textiles



NORFAB AL7 Aluminized Fabric Data Sheet

Style	05PT339-58-AL7
Base Fabric	Twaron®/OPF/Kynol® Blend
Color/Appearance	Dark Green, Aluminized 1 side
Style	Plain Weave
Fabric Weight (oz/yd², average)	7.5 oz/yd ² (254 gm/m ²)
Fabric Thickness (in)	0.015
Warp Strength (lbs) Grab Method	190
Filling Strength (lbs) Grab Method	70
Flamability - After Flame (sec)	1
Flamability - Char length (in)	3
Adhesion after Wet Flex	Pass
Reflectivity after Abrasion (seconds)(ASTM F1939)	25
RPP Rating (cal/cm²)	50
Molten Aluminum Splash (ASTM F955)	Pass

All data +/- 10%. All data intended as general information and no warranties, guarantees, or claims of fitness for use are expressed or implied by NORFAB Corp. 514



1310 Stanbridge Street,

Box 830, Norristown, PA 19404-0830 U.S.A.

Tel: 610-275-7270 • 800-441-9680 • Fax: 610-277-6106

Email: sales@norfab.com • www.norfab.com

